## 一种含蒽末端支化 PEEK 齐聚物的合成

那莹,牛亚明,王贵宾,姜振华<sup>\*</sup>

(吉林大学化学学院长春 130012)

超支化聚合物由于其独特的物理化学性质与简便的制备过程成为近 10 多年 来高分子科学研究的热点。曾超支化聚合物的三维分子结构的外围分布着大量可 反应性基团,易于进行进一步功能化。其低链缠结的特性与功能基团的外围分布 可使所获得的功能材料具有更高的功能活性。

超支化聚合物应用为光敏材料具有广阔的前景。超支化聚合物特有的紧密的 分子结构与低分子链缠结的特点,作为光敏材料的高分子骨架比线性聚合物具有 更大的优势。同时,光敏基团在外围的分布可使其具有更高的光敏性。

因此,我们通过在外围引入蒽环结构,制备了一种新型支化聚醚醚酮(PEEK-An)的齐聚物,并通过IR, MS, DSC, <sup>1</sup>H-NMR 等方法对其进行了表征。

1、实验部分

以间苯三酚为原料,以N,N-二甲基甲酰胺(DMF)为溶剂,按亲核取代反应路线合成如下 PEEK-An 齐聚物。



2、表征:采用 IR, MS, DSC, <sup>1</sup>H-NMR 对该齐聚物进行表征。

从红外光谱可知,1655cm<sup>-1</sup>为羰基伸缩振动,1225 cm<sup>-1</sup>为 Ph-O-Ph 的不对称 伸缩振动,1163 cm<sup>-1</sup>为醚键特征吸收峰,604 cm<sup>-1</sup>,723 cm<sup>-1</sup>,893 cm<sup>-1</sup>为蒽的特 征吸收峰。具有 HPEEK 齐聚物的特征吸收。激光飞行质谱测得该分子的分子量 M = 967,为计算值 966 的 M+1 峰。该分子的 <sup>1</sup>H-NMR 见 Figure 1,氢的归属见 Table 1,从而进一步证明我们已经成功的得到了预期的 PEEK- An 齐聚物。由 DSC 测得 的该 HPEEK 预聚物的熔点为 125 。



参考文献:

1、Tomalia, D.A.; Dvomic, P.R. Nature 1994,372, 617-618

2、 Frechet, J.M.J. Science 1994,263, 1710-1715

## Synthesis of a Novel HPEEK Oligomer containing Anthracene

Ying Na, Yaming Niu, Guibin Wang , Zhenhua Jiang $^{st}$ 

(Engineering Research Center of Jilin University for Super Engineering Plastics, Ministry of Education, College of Chemistry, Jilin University, ChangChun 130012)

Dendrimers, which have precisely hyper-branched architecture coupled with their spherical structures, have attracted great deal of interests due to remarkable availability for applications in many fields. A lot of elaborations have therefore been paid for syntheses of new dendrimers in order to create intriguing functionalities such as photo harvesting antenna effect of aromatic dendrimers. In this communication, a novel HPEEK was successfully prepared. And the properties were studied by IR, DSC, MS and <sup>1</sup>H-NMR.

Keywords: hyper-branched PEEK oligomer anthracene